

# Studies on Stone Mastic Asphalt mixes with Partially Replacement in Addition with Waste Plastic

<sup>1</sup>Uppalapati Arun Kumar, <sup>2</sup>Dr.G.Sreenivasa Reddy

**ABSTRACT**--The present assessment inquires about the benefits of offsetting the stone mastic dark top (SMA) mix in versatile black-top with decimated squander plastic. Standard (without plastic) and the reasonable out SMA mixes were presented to execution of compressive quality tests and split pliable quality tests with moving rate bitumen by weight of mineral aggregate (5% to 6.5%) and by varying rate plastic by weight of mix(5%,10% and 15%). Plastic substance of 10% by weight of bitumen is endorsed for the improvement of the display of Stone Mastic Asphalt mixes. 10% plastic substance empowers an extension in the compressive stood out strain stretch from the customary SMA Mix

**Keywords**-- SMA, Waste Plastic, Void Ratio, Compressive Strength, Split Tensile

## I. INTRODUCTION

### 1.1. General

Stone mastic dark top (SMA) is a stone-on-stone like skeletal structure of gap surveyed all out, sustained together by mastic, which truly is higher spread substance, filler and fiber to diminish the latch channel. This structure improves the quality and the presentation of SMA a lot higher than the thick assessed and open looked into dark top mixes. Significant level of clasp content is basic to ensure the robustness and laying characteristics of SMA.

### 1.2. Air Voids

Air voids are little airspaces or pockets of air that happen between the covered total particles in the last compacted blend. A specific level of air voids is important in all thick reviewed expressway blends to take into consideration some extra asphalt compaction under traffic and to give spaces into which limited quantities of black-top can stream during this ensuing compaction. The suitable level of air voids (in research facility examples) is between 2.0 percent and 4.0 percent for most surface course blends or as required by the proprietor. The sturdiness of a black-top asphalt is a component of the air-void substance. This is on the grounds that the lower the air-voids, the less porous the blend becomes. Too high an air-void substance gives ways through the blend to the passage of harming air and water. A low air-void substance, then again, can prompt flushing, a condition where abundance black-top presses out of the blend to the surface. Thickness and void substance are legitimately related. The higher the thickness, the lower the level of voids in the blend, and the other way around. Employment particulars require asphalt that permits as low an air void substance as is viable, around 8.0 percent.

---

<sup>1</sup> Department of Civil Engineering, JNT University Anantapur, Anantapur-515002, A.P, India, arunuppalapati@gmail.com

<sup>2</sup> Department of Civil Engineering, KSRMCE, Kadapa-516003, A.P, India, transgsr@gmail.com

### *1.3. Difference between SMA & Conventional Mixes*

SMA is adequately used by various countries on the planet as significantly channel safe bituminous course, both for spread (moderate) and wearing course. The noteworthy difference between common mixes and SMA is in its essential skeleton. The SMA has high percent around 70-80 percent of coarse aggregate in the mix. This assembles the interlocking of the sums and gives better stone to stone contact which fills in as weight passing on part in SMA and from now on gives better channel resistance and toughness. On the other hand, standard mixes contain around 40-60 percent coarse aggregate. They have stone to stone contact, anyway it much of the time suggests the greater grains fundamentally float in a structure made out of tinier particles, filler and dark top substance. The constancy of the mix is chiefly obliged by the association and inside scouring of the system which supports the coarse sums. It can be sought after from diagram of the grain size dispersal of the mixes given underneath.

The resulting qualification lies in the spread substance which lies between 5-6 percent for standard mixes. Underneath this the mix ends up being incredibly unstable. Over this percent will provoke unexpected drop of security considering the way that the folio fills all the available voids and the extra latch makes the aggregates to skim in spread system. The SMA uses uncommonly high percent of clasp > 6.5 percent which is attributed to filling of more proportion of voids present in it, in light of high coarse all out skeleton. The high bitumen content adds to the life expectancy of the black-tops.

The third differentiation is the use of settling included substances in SMA which is credited to the garnish off of tremendous no of voids in SMA so as to diminish the channel down on account of pith of high bitumen content. In spite of what may be normal, there is no offsetting pro in conventional mixes since the bitumen content is moderate, which just viably fills the moderate proportion of voids and limiting the sums.

### *1.4. Motivation*

The budgetary advancement of a system is poor upon thoroughfare progression to improve adaptability. In any case, improperly orchestrated, arranged, created, and kept up roadways can agitate the social and monetary qualities of any size system. Ordinary unpleasant impacts to expressway progression consolidate mischief of living space and bio-conventional assortment, creation of air and water sully, uproar and vibration age, damage of trademark scene, and the devastation of a system's social and social structure. Expressway system must be created and kept up to high qualities and measures.

### *1.5. Objectives of the Study*

This paper focuses thinking about Objectives, advancement material structure, economy achieving by using waste materials and ideal conditions over the customary mixes. Exact estimation of all out degree is essential for a predominant appreciation of its effect on the stack passing on point of confinement of a dark top mix and Volumetric assessment of the aggregate. study looks at the upsides of offsetting the stone mastic dark top (SMA) mix in versatile black-top with waste plastic and use of low thickness polyethylene fundamental nourishment thing packs in the SMA.

### *1.6. Organization of the Report*

Interstate structures produce the most noteworthy cost in human harm and going, as around 50 million individuals are hurt in car accidents reliably, barring the 1.2 million passings. Road traffic harm is the single driving explanation behind unforeseen downfall in the underlying five numerous long stretches of human life.

The administrator of security is a methodical system that tries to reduce the occasion and reality of vehicle crashes. The man/machine correspondence with road traffic structures is shaky and speaks to a test to freeway prosperity the board.

## II. MATERIALS & METHODS

1. 12.5mm coarse aggregates
2. Lime( max filler to cover (F/B)ratio 1/2 to 1/5)

Lime is a calcium-containing inorganic mineral made basically out of oxides, and hydroxide, typically calcium oxide and furthermore calcium hydroxide. It is moreover the name for calcium oxide which occurs because of coal-wrinkle fires and in balanced limestone xenoliths in volcanic ejecta.[1] The word lime begins with its most reliable use as building mortar and has the sentiment of staying or following.

3. Stone residue ( max filler to binder (F/B)ratio 1/2 to 1/5)

Stone residue, generally called shake powders, shake minerals, shake flour, soil remineralization, and mineral fines, includes finely squashed shake, took care of by standard or mechanical techniques, containing minerals and pursue segments commonly used in regular developing practices.

4. Bitumen (5% 5.5% 6%, 6.5% are used)

Bitumen, generally called bitumen is a tenacious, dull, and significantly thick liquid or semi-solid sort of oil. It may be found in like manner stores or may be a refined thing, and is classed as a pitch. Preceding the twentieth century, the term asphaltum was in like manner used.

5. Waste plastic polymer (low density polyethylene grocery bags) (5%, 10% 15%)

Plastic is material including any of a wide extent of made or semi-designed regular fuels that are adaptable along these lines can be formed into solid articles. Flexibility is the general property of all materials which can turn irreversibly without breaking in any case, in the class of malleable polymers, this hops out at such a degree, that their genuine name gets from this specific limit. Plastics are usually regular polymers of high nuclear mass and habitually contain various substances. They are regularly designed, most normally got from petrochemicals, regardless, an assortment of varieties are created utilizing unlimited materials, for instance, polylactic destructive from corn or cellulose from cotton linters.

6. Wax

Waxes are a contrasting class of regular bothers that are lipophilic, adaptable solids near encompassing temperatures. They consolidate higher alkanes and lipids, usually with dissolving centers above around 40 °C (104 °F), melting to give low consistency liquids. Waxes are insoluble in water anyway dissolvable in characteristic, nonpolar solvents. Standard waxes of different sorts are made by plants and animals and occur in oil.

## III. LABORATORY TESTING

### *3.1 Properties of Bitumen Aggregates are as follows*

TABLE I. PROPERTIES OF BITUMEN AGGREGATES

Penetration @ 25 Degree Centigrade	64
Ductility @ 25 Degree Centigrade	110
Softening Point	51 <sup>o</sup> C
Aggregate Impact Value	16%
Los Angeles Abrasion Value	35%
Specific Gravity of Aggregate	2.67
Water Absorption of Aggregate	2.37
Aggregate Crushing Value	37%

### 3.2 Compressive strength test

Test for compressive quality is completed either on shape or chamber. Diverse standard codes recommend strong chamber or strong 3D Square as the standard model for the test. Compressive quality is the limit of material or structure to pass on the piles on its surface with no break or preoccupation. A material under strain will when all is said in done diminish the size, while in strain, size expands. Compressive quality condition for any material is the stack applied at the motivation behind failure to the cross-section zone of the face on which weight was applied. The estimations of compressive strength test are been given in the below, reports and talks.

### 3.3 Split Tensile strength test

This property for concrete identifies with its pressure quality. This is acquired by performing split malleable test on solid example. The solid example in this test is taken as round and hollow fit as a fiddle. Rigidity for solid example is characterized as the malleable burdens created because of use of the compressive burden at which the solid example may split. Compose the articulation for ascertaining the split elasticity  $T_{sp} = 2P/\pi DL$  of the solid. Here, the term P is applied burden on the solid, D is round and hollow example width and L is tube shaped example length. Split elasticity for concrete is given as beneath. Here, the term fck alludes to trademark quality of concrete.

### 3.4. Percent Voids Filled with Asphalt (VFA)

The VFA is the level of voids in the compacted total mass that are loaded up with black-top concrete. It is synonymous with the black-top void proportion. The VFA property is significant as a proportion of relative solidness, yet in addition in light of the fact that there is an incredible connection among's it and percent thickness. In the event that the VFA is excessively low, there isn't sufficient black-top to give sturdiness and to over-densify under traffic and drain. In this way, the VFA is a significant plan property. Most DOT determinations require 70-80 during the plan stage; this necessity is proposed for the blend during the structure stage just and is regularly not a generation prerequisite. HMA intended for moderate to overwhelming traffic may not pass the VFA necessity with a generally low percent of air voids in the field despite the fact that the measure of air voids is inside the worthy range. Since low air void substance might be extremely basic as far as opposing changeless disfigurement, the VFA prerequisite maintains a strategic distance from those blends that are defenseless to rutting in substantial rush hour gridlock circumstances.

### 3.5. Voids in the Mineral Aggregate (VMA)

Voids in the mineral Aggregate (VMA) are the air-void spaces that exist between the total particles in a compacted clearing blend, incorporating spaces loaded up with black-top. VMA speaks to the space that is accessible to oblige the black-top and the volume of air voids vital in the blend. The more VMA in the dry total, the more space is accessible for the film of black-top. In light of the way that the thicker the black-top film on the total particles the more tough the blend, explicit least prerequisites for VMA are determined in many determinations. Least VMA qualities ought to be clung to with the goal that a tough black-top film thickness can be accomplished. Expanding the thickness of degree of the total to a point where underneath least VMA values are gotten prompts slim movies of black-top and a dry looking, low sturdiness blend. Along these lines, conserving in black-top substance by bringing down VMA is in reality counter-beneficial and negative to asphalt quality.

## IV. RESULTS & DISCUSSIONS

TABLE II. VOID ANALYSIS OF CONVENTIONAL MIX

S. No.	Bitumen Content	Bulk Specified Gravity	Air Voids	Voids in Mineral Aggregate	Voids filled Bitumen
1	5	2.424	7.508	20.513	56.74
2	5.5	2.448	7.05	20.325	63.113
3	6	2.465	6.371	20.19	70.01
4	6.5	2.481	5.87	19.85	79.52

TABLE III. RESULTS OF TENSILE STRENGTH TEST

Mixes	Tensile Strength in N/mm <sup>2</sup>			
	Sample 1	Sample 2	Sample 3	Average
Conventional Bitumen Mix	0.69	0.63	0.65	0.656667
5% Plastic Mix Bitumen	0.85	0.79	0.81	0.816667
10% Plastic Mix Bitumen	1.25	1.48	1.11	1.28
15% Plastic Mix Bitumen	0.92	0.89	0.85	0.886667

TABLE IV. VOID PLASTIC MIXED

ANALYSIS OF 5% BITUMEN MIX

S.No	Bitumen Content	Bulk Specified Gravity	Air Voids	Voids in Mineral Aggregate	Voids filled Bitumen
1	5	2.431	7.21	19.98	57.65
2	5.5	2.457	6.74	19.712	64.48
3	6	2.478	5.88	19.27	71.87
4	6.5	2.487	5.42	18.85	81.25

TABLE V. VOID ANALYSIS OF 10% PLASTIC MIXED BITUMEN MIXES

S.No	Bitumen Content	Bulk Specified Gravity	Air Voids	Voids in Mineral Aggregate	Voids filled Bitumen
1	5	2.478	6.85	19.35	59.04
2	5.5	2.494	6.17	19.11	66.37
3	6	2.519	5.36	18.56	74.53
4	6.5	2.531	4.92	18.27	84.12


TABLE VI. VOID ANALYSIS OF 15% PLASTIC MIXED BITUMEN MIX

S.No.	Bitumen Content	Bulk Specified Gravity	Air Voids	Voids in Mineral Aggregate	Voids filled Bitumen
1	5	2.455	7.13	19.72	58.54
2	5.5	2.479	6.54	19.54	65.73
3	6	2.495	5.68	18.95	72.69
4	6.5	2.504	5.23	18.63	82.87


TABLE VII. RESULTS OF COMPRESSION STRENGTH TEST

Mixes	Compressive Strength in N/mm <sup>2</sup>			
	SPC 1	SPC 2	SPC 3	AVG
Conventional Bitumen Mix	4.019	4.126	4.23	4.125
5% Plastic Mix	4.929	5.09	5.1	5.039667

Bitumen				
10% Plastic Mix				
Bitumen	8.13	7.763	6.396	7.429667
15% Plastic Mix				
Bitumen	6.89	7.001	6.921	6.937333



**Figure 1.** Compressive Strength Vs % of Replacement Bitumen mix



**Figure 2.** Tensile Strength Vs % of Replacement Bitumen mix

## V. CONCLUSIONS

Usual bitumen concrete is possessing compressive strength of 4.125 N/mm<sup>2</sup>. Whereas polymer mix SMA in 5%, 10%, 15% is possessing compressive strength of 5.04 N/mm<sup>2</sup>, 7.43 N/mm<sup>2</sup>, 6.94 N/mm<sup>2</sup>.

For 5% substitute of polymer ravage in the Usual SMA the compressive strength is improved to 22%. For 10% substitute of polymer ravage in the Usual SMA the compressive strength is improved to 80%. For 15% substitute of polymer ravage in the Usual SMA the compressive strength is improved to 68%.

Usual bitumen concrete is possessing Tensile strength of 0.657 N/mm<sup>2</sup>. Whereas polymer mix SMA in 5%, 10%, 15% is possessing compressive strength of 0.817 N/mm<sup>2</sup>, 1.28 N/mm<sup>2</sup>, 0.887 N/mm<sup>2</sup>.

For 5% substitute of polymer ravage in the Usual SMA the tensile strength is improved to 24.35%. For 10% substitute of polymer ravage in the Usual SMA the tensile strength is improved to 94.82%. For 15% substitute of polymer ravage in the Usual SMA the tensile strength is improved to 35%.

For substitute of polymer ravage in SMA compressive and tensile strength is improving. For 10% substitute of polymer ravage it is enhancing the peak strength. For 15% again it is dropping from peak node.

## REFERENCES

1. L.R Schroeder, "The Use of Recycled Materials in Highway construction", Public Roads, Vol 58(Issue 2), 1994.
2. Sunil Bose, Sridhar Raju , "Utilization of waste plastic in Bituminous Concrete mixes", Roads and Pavements, (2004),
3. L.Flynn, "Recycled Plastic finds it home in Asphalt Binder", Roads and Bridges , (1993)
4. S.E Zorrob, and L. B Suparama " Laboratory Design and Investigation of Proportion of bituminous Composite Containing Waste Recycled Plastics aggregate Replacement (Plastiphalt)", CIB Symposium on construction and Environment Theory into Practice
5. D N Little, "Enhancement of asphalt concrete mixtures to meet structural requirements through the addition of recycled polythene, use of waste materials in hot mix asphalt", ASTM Special Tech Publication,1193(1993)
6. .H Denning, & J Carswell, "Assessment of Novophalt as a Binder for Rolled Asphalt Wearing Course", TRRL Report 1101, Transport and Road research Laboratory, Crowthorne (England), 1983.
7. J.L Goodrich, "Asphalt and Polymer Modified Asphalt related to the performance of Asphalt Concrete Mixes", Association of the Asphalt Paving Technology, 1998.
8. Gupta Dr. Y.P., Shailendra Tiwari, Pandey J.K. Utilisation of Plastic Waste in Construction of Bituminous Roads. NBM & CW, 2010, March, p. 92
9. Bale Amol S. Potential reuse of plastic waste in road construction: a review. International Journal of Advances in Engineering & Technology (IJAET), 2011, No. 2, pp. 233-236.
10. Bindu C.S., Beena K.S. Waste plastic as a stabilizing additive in Stone Mastic Asphalt. International Journal of Engineering and Technology, 2010, 2.6, pp.379-387.
11. Jassim Hamed M., Omar T. Mahmood, Sheelan A. Ahmed. Optimum use of plastic waste to enhance the Marshall properties and moisture resistance of hot mix asphalt. International Journal Engineering. Trends and Technology, 2014, No. 7, pp. 18-25.



12. Israa Saeed Jawad Al-Haydari and Ghadah Ghassan Masued (2017), "Benefit of using Expanded Polystyrene Packaging Material to Improve Pavement Mixture Properties", *Applied Research Journal*, Vol.3 (Issue 11), PP.332-342.
13. Dr. Hamed M. Jassim, Omar T. Mahmood and Sheelan A. Ahmed (2014), "Optimum use of Plastic Waste to Enhance the Marshall Properties and Moisture Resistance of Hot Mix Bitumen", *International Journal of Engineering Trends and Technology*, Vol.7, No.1, P.223.
14. Sabina, Tabrez A. Khan, Sangita, D. K. Sharma and B. M. Sharma (2009), "Performance Evaluation of Waste Plastic/Polymer Modified Bituminous Concrete Mixes", *Journal of Scientific & Industrial Research*, Vol.68 (11) , PP.975-979.
15. Dipankar Sarkar and Manish pal (2016)," A Laboratory Study Innovating use of Brick Aggregate along with Plastic Modified Bitumen in Preparation of Bituminous Concrete for The Road of Tripura", *ARPJN Journal of Engineering and Applied Science*, vol.11, no.1, pp 570-576
16. A. U. Ravi Shankar, K. Koushik and Goutham Sarang (2013), "Performance Studies On Bituminous Concrete Mixes Using Waste Plastics", *Highway Research Journal*, Vol.6, No.1, pp 1-11
17. Pareek A.,Gupta T. and Sharma R.K (2012), "Performance of polymer modified bitumen for flexible pavement", *International Journal of Structural and Civil Engineering Research*, Vol. 1, No.1. pp 77-86